

# AWNING & ROOFING

## MULTIPURPOSE AWNING CAULK



ISO 9001

### DESCRIPTION:

**x'traseal®** MULTIPURPOSE AWNING CAULK IS ONE PART SEALANT THAT OFFER EXCELLENT ADHESION, OUTSTANDING DURABILITY AND EXCELLENT GUNNABILITY FOR GENERAL SEALING APPLICATION.

### FEATURES:

- ◆ OUTSTANDING DURABILITY
- ◆ ONE PART NO MIXING
- ◆ LOW VOC (VOLATILE ORGANIC COMPOUND)
- ◆ FLEXIBLE ( $\pm 3\%$ )
- ◆ EXCELLENT GUNNABILITY ( $-20^{\circ}\text{C}$  TO  $50^{\circ}\text{C}$ )
- ◆ WEATHER PROOF
- ◆ LOW SHRINKAGE
- ◆ NO SAGGING
- ◆ PRIMERLESS ADHESION TO MOST MATERIALS
- ◆ PAINTABLE AFTER CURED

### USES:

GENERAL JOINT SEALING IN EXTERNAL WALLING, WINDOW AND DOOR FRAMES, ROOFS AND OTHERS.

**WE RECOMMEND PRELIMINARY COMPATIBILITY TESTS PRIOR TO APPLICATION TO ACHIEVE DESIRABLE RESULTS**

### NOT RECOMMENDED FOR:

MULTIPURPOSE AWNING CAULK IS NOT SUITABLE FOR HIGH JOINT MOVEMENT SUBSTRATE (MORE THAN  $\pm 3\%$  JOINT MOVEMENT).

### COLOUR:

WHITE, GREY AND BLACK. OTHER COLOURS ARE AVAILABLE UPON REQUEST

### APPLICATION:

- ◆ SURFACE MUST BE CLEAN AND DRY.
- ◆ MASK SMOOTH SURFACE TO SIMPLIFY CLEAN UP.
- ◆ USE APPROVED BACK-UP MATERIAL IN JOINT.
- ◆ CUT NOZZLE TO DESIRED SIZE.
- ◆ INSERT CARTRIDGE INTO CAULKING GUN.
- ◆ PUSH SEALANT AHEAD FOR UNIFORM BEAD.
- ◆ TOOL WITHIN 10 MINUTES.
- ◆ CLEAN OFF EXCESS SEALANT WITH MINERAL SPIRIT.

### CURING TIME:

MULTIPURPOSE AWNING CAULK WILL TACK FREE IN APPROXIMATELY 24 HOURS.

### SPECIFICATION:

CURING SYSTEM	OXIDIZING
APPEARANCE	NON-SAGGING PASTE
ODOUR	OLEO-RESINOUS
SPECIFIC GRAVITY	1.60 $\pm$ 0.3
MAX. JOINT MOVEMENT	$\pm 3\%$
SHRINKAGE	5 % APPROX.
TACK FREE TIME	24 HOURS APPROX.
APPLICATION TEMP.	4 $^{\circ}\text{C}$ TO 50 $^{\circ}\text{C}$
SERVICE TEMP.	-5 $^{\circ}\text{C}$ TO 60 $^{\circ}\text{C}$
SHELF LIFE	12 MONTHS

### STORAGE:

MATERIAL SHOULD BE STORED IN A DRY AND COOL PLACE BETWEEN +5 $^{\circ}\text{C}$  TO +30 $^{\circ}\text{C}$ .

### CAUTION:

READ AND UNDERSTAND MATERIAL SAFETY DATA SHEET OF THIS PRODUCT BEFORE HANDLING OR USING.

*This information is provided in good faith and is believed accurate based on a review of current composition and information supplied by vendors. No warranty is expressed or implied. Liability is expressly disclaimed.*

